

Trade Spec Sheet

Handmade ceramic surfaces from East Flanders, Belgium. Prepared batches, glaze finishing, and project commissions by direct inquiry.

<p>Material Character</p> <p>Handmade ceramic tile surfaces with visible variation in tone, glaze movement, relief, edge character, and slight dimensional difference. Variation belongs to the finished work.</p>	<p>Typical Uses</p> <p>Interior wall surfaces, kitchens, bathrooms, shower areas, fireplace surrounds, hospitality accents, and project-specific architectural surfaces. Exterior use is reviewed individually.</p>	<p>Sample Policy</p> <p>Samples may be supplied for active projects once the intended surface direction is known. They indicate glaze family and material behaviour; final batches remain naturally varied.</p>	<p>Lead Times</p> <p>Prepared bisque stock may reduce timing where available. Larger commissions, relief surfaces, and custom glaze directions should be discussed at least 8 weeks ahead.</p>	<p>Annual Production</p> <p>Approximately 600 m² of tiles are produced each year, keeping the work limited and tied to atelier rhythm.</p>
<p>Drying & Firing</p> <p>Tiles are dried between pieces of wood, bisque fired at 1080°C, and glaze fired at 1180°C.</p>	<p>Finish Options</p> <p>Flat glazed surfaces, selected relief surfaces, glaze-family selection, and restrained custom glaze directions. Strict factory repetition is not the intended character.</p>	<p>Installation Notes</p> <p>Blend tiles across the batch before installation. Substrate, waterproofing, adhesive, grout, movement joints, and final suitability must be confirmed by the appointed installer.</p>	<p>Care Notes</p> <p>Use mild non-abrasive cleaning. Avoid harsh acids, strong alkalis, abrasive pads, and snagging cloths on relief surfaces. Relief may require a soft-bristle brush.</p>	<p>Inquiry Requirements</p> <p>Share intended setting, approximate surface area, surface family, project location, timing, and whether samples are required for client or material-board review.</p>